

WHAT IS CLAIMED IS:

1. A rubber composition for tire comprising from 0.5 to 12 parts by weight of paper relative to 100 parts by weight of a rubber component.
2. The rubber composition according to claim 1, wherein said paper is newspaper waste.
3. The rubber composition according to claim 1, further comprising from 10 to 100 parts by weight of carbon black relative to 100 parts by weight of the rubber component.
4. A pneumatic tire comprising the rubber composition for tire according to claim 1 in a tread portion and/or a bead apex.
5. A rubber composition for tire comprising from 0.5 to 12 parts by weight of paper and from 5 to 100 parts by weight of silica relative to 100 parts by weight of a rubber component.
6. The rubber composition for tire according to claim 5, further comprising from 10 to 100 parts by weight of carbon black relative to 100 parts by weight of the rubber component.
7. The rubber composition for tire according to claim 5, further comprising silane coupling agent.
8. A pneumatic tire comprising the rubber composition for tire according to claim 5 in a tread portion and/or a bead apex.
9. A rubber composition for tire comprising from 0.5 to 12 parts by weight of paper, from 5 to 100 parts by weight of silica, and from 2 to 15 parts by weight of short fiber relative to 100 parts by weight of a rubber component.

10. The rubber composition for tire according to claim 9, further comprising from 3 to 15 parts by weight of a powder product containing a cellulose material relative to 100 parts by weight of the rubber component.

11. A pneumatic tire comprising the rubber composition for tire according to claim 9 in a tread portion and/or a bead apex.

0911734.07501
T052/0.4E/T660